LABORATORIO TRENTINO s.r.l.
Via degli Artigiani, 34- Z.I. Cirè
38057 PERGINE VALSUGANA (TN)
Tel. 0461/509040 – Fax 0461/509020
E-mail: info@laboratoriotrentino.it

TEST REPORT

N. 485-01/09-i

Foglio 1 di 1
Sheet of
Data 18/09/2012
Date

CUSTOMER: **SAB S.P.A.**
Via Salvo d'acquisto, 9 - Zona Ind.le
61048 S.Angelo in Vado (PU), Italy

Re: **FLAME RESISTANCE DETERMINATION FOR SAMPLES OF A PLASTIC ARTEFACT.**

1.0 PREMISE

1.1 The customer delivered to the laboratory n°1 set of parts of a plastic material in the form of an injection moulded part.
The parts were sampled and marked by the Customer as:

1.1.1 Sample – self-extinguishing Polypropylene Rialti – for channel SABDRAIN 200x300x1000.

2.0 TESTS REQUESTED AND CARRIED OUT

In agreement with the Customer the following tests were made:

2.1 Determination of the flame resistance, in analogy with standard UL 94 method V0-1-2.

3.0 RESULTS OBTAINED

3.1 *Resistance to the flame*

Classification	Ignition time I 10 sec	Ignition time II 10 sec	Dripping	Cotton ignites
V0	<10 sec	<10 sec	No	No
V1	<30 sec	<30 sec	No	No
V2	<30 sec	<30 sec	Yes	Yes

Sample – Self-extinguishing Polypropylene Rialti.

Sample	Ignition time I (s)	Ignition time II (s)	Dripping	Cotton ignites
Test 1	4	5	Yes	No
Test 2	3	5	Yes	No
Test 3	3	4	Yes	No
Test 4	5	3	Yes	No
Test 5	4	5	No	No

Classification UL: **V2**

Test results refer only to the material tested. Partial reproduction of this document without our written approval is forbidden
I risultati di prova si riferiscono solo al materiale provato. È vietata la riproduzione parziale del presente documento senza Ns. approvazione scritta.

Prove eseguite da / Test conducted by	Controllato da / Controlled by	Ispettori / Ispectors
LABORATORIO TRENTINO s.r.l.	LABORATORIO TRENTINO s.r.l. SIGHEL per. ind. SERGIO	
Firma / Signature	Firma / Signature	Firma / Signature .....